

Springer Liner Board

BLEACHED BACK FOLDING BOX BOARD (GC)

THE BOARD:

- Suitable for lamination
- Approved for direct food contact
- Excellent graphic reproduction using litho, Screen and digital.

OUR SERVICE:

- Available from reels in 5 working days
- Sheet stock available in 48 hours

Specifications

		Springer Liner Board
Grammage	g/m ²	205
Thickness	µm	320
Cobb (g/m ² 60s)	print side	28
	reverse	25
Taber Stiffness L&W 5% mN m	MD	17.4
	CD	7.2
Tolerances		Moisture: 6.5% Thickness ± 4%, max ± 20µm (ISO 534)

Construction

