

Omni-kote® and Pearl-kote®

COATED UNBLEACHED SULPHATE BOARD

THE BOARD:

- Suitable for most carton applications
- Approved for direct food contact
- High stiffness - can drop 2-3 calipers against other boards
- Excellent graphic reproduction

OUR SERVICE:

- Available from reels in 5 working days
- Making orders available

Specifications

		Omni-kote®				Pearl-kote®				
Grammage	g/m ²	305	330	360	390	420	455	490	525	560
Thickness	µm	356	406	457	508	559	610	660	711	762
Caliper	pt	.014	.016	.018	0.20	.022	.024	.026	.028	.030
Taber Stiffness mN m	MD	nom 15.2 min 12.9	nom 20.6 min 17.6	nom 28.4 min 24.2	nom 34.8 min 29.6	nom 44.1 min 37.6	nom 54.9 min 46.7	nom 66.7 min 56.7	nom 79.9 min 68.0	nom 93.7 min 79.9
	CD	nom 7.8 min 6.7	nom 9.8 min 8.3	nom 13.7 min 11.7	nom 16.2 min 13.7	nom 20.6 min 17.6	nom 27.0 min 22.9	nom 31.9 min 27.1	nom 38.7 min 33.0	nom 46.6 min 39.6
Tolerances	Thickness ± 4%, max ± 20µm (ISO 80.2)									

Construction

